

# OUTDOOR STRETCH DOUBLE

## **TECHNICAL DATA SHEET**

June 2018

Outdoor Stretch is a double-coated, flame-retardant and waterproof stretch fabric ideal for outdoor applications. This outdoor fabric is 145 cm wide and is flexible enough to create any 3D shape. It can be used as dim-out fabric and even works as a projection surface. The double-sided white and grey fabric is flame retardant and can be custom-sewn in our workshop or custom-printed on demand.

» ARTICLE CODE

2965 0145 0659

WIDTH

145 cm

» LENGTH

» WEIGHT

± 100 m

290 g/m<sup>2</sup>

COMPOSITION

40% PES + 60% PU coating

» CARE INSTRUCTIONS









» FLAME RESISTANCE

NFP 92-503 CLASS M2 **DIN 4102** CLASS B1

**WASHING** 

Washing (40°C or 95°C) must be done with neutral detergents; softening agents are not allowed. Undyed fabrics may be washed following the ISO 6330 norm, Part 9A and dyed

fabrics following the ISO 6330 norm Part 3A.

**DISINFECTIONS** 

In general, the PVC-coated products resist well to most of the currently used surface disinfectants. Nevertheless, we advise to test the particular surface disinfectant in advance or to contact us in case.

**DRYING** 

Adequate drying is a crucial factor in the care and maintenance of coated articles. Drying may be effected by hanging out, spinning or tumbling at temperatures up to 60°C. Do

not press or mangle!

» STORING

Store in a dry area, at room temperature. Avoid excessive pressure and contact with non-colourfast materials. Try not to expose the PVC-Coating to excessive sunlight (UV-

radiation).



# **OUTDOOR STRETCH DOUBLE**

# **TECHNICAL DATA SHEET**

June 2018

#### » SHRINKAGE AFTER WASHING

ISO 5077: 1984 Warp: 0 [+/-4] % Weft: 0 [+/-2] %

#### » TEAR STRENGTH

ISO 4674A1: 1977 Warp: 50 N Weft: 45 N

#### » BREAKING STRENGTH

ISO 13934: 1999 Warp: 400 N/5cm Weft: 300 N/5cm

#### » BREAKING EXTENSION

ISO 13934: 1999 Warp: 90 % Weft: 120 %

### **»** WATERPROOFNESS

ISO 811: 1981 Before washing: 2000 mm After washing: 2000 mm

### » AVAILABLE COLOURS



0659